

IGS3723

two part insulating glass silicone sealant

Product Description

IGS 3723 insulating glass sealant is a two-component silicone which cures to form a high strength, high modulus sealant exhibiting the following features:

- Excellent adhesion to glass, most reflective glass coatings, aluminum and galvanized steel spacers.
- Variable ratio allowing for cure rate adjustment.
- High application rate at low pumping pressures (reduces pump wear)
- Excellent filling and tooling characteristics.
- Low sag or slump. Allows use on automatic sealing equipment.
- Low odour.
- No kit matching required.
- Compatible with UltraGlaze* structural glazing sealants.
- Non-Flammable curing agent.

Key Features and Benefits

Packaging

IGS 3723 component A is available in 265.4 kg drums.
IGS 3723 component B is available in 20.4 kg pails.

Colour

IGS 3723 Insulating Glass Sealant is available in black only.

Basic Uses

IGS 3723 insulating glass sealant is designed for use as an insulating glass secondary seal and is easily dispensed using readily available plural component pumping equipment. Only minor modifications to existing silicone plural component pumping system are required.

Limitations

IGS 3723 insulating glass sealant should be used in the fabrication of insulating glass where the dual seal method of fabrication is used. The moisture vapour transmission rate of silicone sealants is sufficiently high as to preclude their use in the fabrication of single seal insulating glass units. The dual seal fabrication method requires the use of a polyisobutylene primary seal with soldered, welded or butyl injected spacer frame corners.

Prior to production use, a sample of base (A component) and curing agent (B component) should be taken from each lot of material to be used, weighed to proper A to B ratio, hand mixed, and checked for proper tack-free time and thick section cure rate prior to placing in production.

Momentive Performance Materials is an exclusive licensee of General Electric. Momentive Performance Materials provides versatile materials as the starting point for its creative approach to ideas that help enable new developments across hundreds of industrial and consumer applications.

We are helping customers solve product, process, and performance problems; our silanes, fluids, elastomers, sealants, resins, adhesives, urethane additives, and other specialty products are delivering innovation in everything from car engines to biomedical

devices. From helping to develop safer tires and keeping electronics cooler, to improving the feel of lipstick and ensuring the reliability of adhesives, our technologies and enabling solutions are at the frontline of innovation.



Exclusive
Licensee

IGS3723 two part insulating glass silicone sealant

Typical Product Data

Uncured Properties	Component A	Component B
Colour	White	Black
Specific Gravity	1.40	1.00
Mixed Compound Properties - Ratio by weight 12.5 : 1		
Colour	Black	
Specific Gravity	1.37	
Snap Time	20 - 50 minutes	
Sag/Flow	2 mm max.	
Corrosiveness	Non-corrosive	
Cured Properties - 7 days @ 23°C, 50% RH		
Shore A Hardness	43	ISO 868
Tensile Strength, MPa	2.1	ISO 37, S 2
Elongation at Break, %	200	ISO 37, S 2
Lap Shear Aluminium, MPa	0.9	
Lap Shear Glass, MPa	0.9	
Cold Flow	Negligible	
Heat Resistance, °C	150	

Technical Data

IGS 3723 insulating glass sealant exhibits typical silicone sealant resistance to the environments usually encountered in insulating glass applications. These environments include ultra violet radiation, ozone, high and low temperature extremes and hydrolytic stability (high temperature and humidity).

IGS 3723 insulating glass sealant is compatible with many types of coated high performance glass used in insulating glass fabrication. Also, it exhibits compatibility with many types of glazing sealants, particularly silicone glazing sealants. Momentive Performance Materials¹ should be contacted with regard to specific glass types and glazing sealants for adhesion and compatibility information.

Instructions for Use

Method of Application

IGS 3723 insulating glass sealant should be mixed and dispensed using two-component mixing equipment which is readily available from several equipment manufacturers. This equipment is specially designed to meter proper proportions of A base and B curing agent, mix in an air-free environment and dispense at the proper pressures and volumes to insure air-free mixed material. Hand mixing is not recommended.

Consult Momentive Performance Materials¹ regarding suggested pumping equipment start-up and shutdown procedures which cover proper operating pressures, mixing devices and purging requirements.

Kit matching of the A and B IGS 3723 insulating glass sealant components is not required.

The B curing agent component is moisture sensitive and should not be exposed to the atmosphere. The curing agent may require minimal hand mixing before placing container in pumping equipment.

Cure rate may be adjusted by changing the A base to B curing agent ratios. IGS 3723 sealant may be used with A to B ratios from 13:1 to 9:1 by weight (9.3:1 to 6.4:1 by volume).

Handling and Safety

Precautions

Material Safety Data Sheets are available upon request from Momentive Performance Materials.¹ Similar information for solvents and other chemicals used with Momentive Performance Materials¹ products should be obtained from your suppliers.

When solvents are used, proper safety precautions must be observed. All solvents must be used only in well ventilated areas. Exposure to high vapor concentrations must be avoided. When flammable solvents are used, storage, mixing and use must be in areas away from heat, sparks, flame or other sources of ignition.

The A and B components of IGS 3723 insulating glass sealant may cause mild eye irritation upon prolonged contact. In the case of eye contact, immediately flush eyes with large quantities of water for at least 15 minutes and contact physician if irritation persists. This material should not be used in contact with foods, drugs or cosmetics.

IGS3723 two part insulating glass silicone sealant

Storage and Warranty Period

Shelf life for the A-part is 18 months and for the B-part 12 months from date of manufacture (see use before date on compliance report) when stored in original, unopened containers below 25°C in a dry place. Storage outside in freezing conditions or above 25°C should be avoided.

Availability

IGS 3723 insulating glass sealant is available on a direct basis from Momentive Performance Materials.¹ For availability and cost information, consult your nearest Momentive Performance Materials¹ sales office.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.momentive.com or, upon request, from any Momentive Performance Materials¹ representative. Use of other materials in conjunction with Momentive Performance Materials¹ products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Emergency Service

Momentive Performance Materials¹ maintains an around-the-clock emergency service for its products. The American Chemistry Council (CHEMTREC), Transport Canada (CANUTEC), and the Chemical Emergency Agency Service also maintain an around-the-clock emergency service for all chemical products:

<u>Location</u>	<u>GE Branded Products</u>	<u>All Chemical Products</u>
Mainland U.S., Puerto Rico	518.233.2500	CHEMTREC: 800.424.9300
Alaska, Hawaii	518.233.2500	CHEMTREC: 800.424.9300
Canada	518.233.2500	CANUTEC: 613.996.6666 (collect) or CHEMTREC: 800.424.9300
Europe, Middle East, Africa	+32.(0)14.58.45.45 (Belgium)	CHEMTREC: +1-703.527.3887 (collect)
Latin America, Asia/Pacific, all other locations worldwide	+518.233.2500	CHEMTREC: +1-703.527.3887 (collect)
At sea	Radio U.S. Coast Guard, which can directly contact Momentive Performance Materials ¹ at 518.233.2500	CHEMTREC: 800.424.9300

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

CUSTOMER SERVICE CENTERS

North America

E cs-na.silicones@momentive.com

- | | | |
|---|-------------------|-------------------|
| • Specialty Fluids | T +1.800.523.5862 | F +1.304.746.1654 |
| • UA, Silanes and Specialty Coatings | T +1.800.334.4674 | F +1.304.746.1623 |
| • RTV's and Elastomers | T +1.800.332.3390 | F +1.304.746.1623 |
| • Consumer Sealants & Construction Sealants and Adhesives | T +1.877.943.7325 | F +1.304.746.1654 |
-

Latin America

E cs-la.silicones@momentive.com

- | | | |
|--|--------------------|--------------------|
| • Argentina & Chile | T +54.11.4862.9544 | F +54.11.4862.9544 |
| • Brazil | T +55.11.4534.9650 | F +55.11.4534.9660 |
| • Mexico & Central America | T +52.55.5899.5135 | F +52.55.5899.5138 |
| • Venezuela, Ecuador, Peru
Colombia & Caribbean | T +58.212.285.2149 | F +58.212.285.2149 |
-

Europe, Middle East, Africa and India

E cs-eur.silicones@momentive.com

T +00.800.4321.1000
T +31.164.225350

Pacific

E cs-ap.silicones@momentive.com

T +1.800.820.0202
T +0.81.276.20.6182 F +81.276.31.6259 |

Worldwide Hotline

T +1.607.786.8131
T +1.800.295.2392 F +1.607.786.8309 |

Visit us at Momentive.com

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*UltraGlaze is a trademark of Momentive Performance Materials Inc.

GE is a registered trademark of General Electric.

Momentive and M-design logo are trademarks of Momentive Performance Materials Inc.

Copyright 2003-2008 Momentive Performance Materials Inc. All rights reserved.